AMENDMENT NO. 1 JULY 2022

TO

IS 1969 (Part 1) : 2018 TEXTILES — TENSILE PROPERTIES OF FABRICS

PART 1 DETERMINATION OF MAXIMUM FORCE AND ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD

(Fourth Revision)

(*Foreword, para* 6) — Insert the following new para after para 6:

'This standard also permits the use of constant rate of traverse (CRT) machine for testing of jute fabrics including their laminates. Details of which are given in National Annex A.'

(*Page* 11, *Annex* B) — Insert the following National Annex A after Annex B:

'**NATIONAL ANNEX A**

(*Foreword*)

For testing of jute fabrics including their laminates, the use of constant rate of traverse (CRT) machine is permitted. The rate of traverse shall be (450 ± 15) mm/min and gauge length shall be 200 mm.'

(TXD 01)

Publication Unit, BIS, New Delhi, India